



Technical Memo – For Public Release

Average Power, Peak Power and Power Density

Background:

In laser applications the energy being delivered or transmitted in unit time should be known. Energy over time is Power. The units here are Joules (J) for Energy, Seconds (s) for time and Watts (W) for power where one Joule per second ($1 \text{ J/s} = 1 \text{ Watt(W)}$). The next extension in analysis is to consider Power Density as in Power per Unit Area.

Obviously, if you have 5W spread over the area of your hand you might barely register the heat. However, if you take that 5W and put it in a fiber optic the diameter of single strand of hair, the Power Density is quite high, high enough, locally, to cause damage, and we need to have an idea of if that might happen.

Considerations start to get tricky fast. For example, is the consideration that of a Continuous Wave (CW) laser or Pulsed laser. A laser is called CW **if its output is nominally constant over an interval of seconds or longer** for example, a laser pointer. Whereas pulsed lasers will deliver energy in discrete pulses that are differentiable.

The problem here is that the terminology and technology has become muddled. Today we often talk in terms of the Power of a laser. Someone might say I have a 5W laser, and in the old days that would mean a CW laser but, not today. If someone tells you they have a 5W laser the next question might be: "is that CW or Average Power?"

If it is true CW, then you know all you need to know. If the answer is Average Power, then the follow up questions are: "What is the Rep Rate and Pulse Width?"

Rep Rate will tell you how many pulses are delivered per second and is usually given in Hertz (Hz) or Kilohertz (KHz) or Megahertz (MHz) or Gigahertz (GHz) etc. Pulse Width will tell how long each pulse lasts, leading to the concept of Peak Power.

Together, the information of CW or Pulsed, Average Power, Pulsed Power, Power per Pulse (Peak Power) and finally a consideration of the size of the fiber being used for this power transmission, resolving the Power to Power Density is critical to determine if the Power Density will exceed the Laser



Induced Damage Threshold (LIDT).

To discuss this further we offer a real-world example:

Example:

An application comes across your desk and starts with the following specifications:

Laser Power: 5W Average Power

Rep Rate: 10KHz

Fiber Diameter: 100μm core

Question: Can the fiber handle it?

Note: We are ignoring wavelength in this example because the calculations we are present are independent of wavelength. However, wavelength should not be fully ignored. In general, the numbers here are based on light around 1000nm. As the wavelength gets shorter, the Laser Induced Damage Threshold (LIDT) decreases linearly. For example, at 532nm, the LIDT is approximately ½ the LIDT at 1064nm.

The specifications above mean there is a laser source that is pulsing 10 thousand times a second (10KHz).

That source has an Average Power of 5W and Average Power is total power delivered in 1 second.

Therefore, adding up the power from 10K pulses would equal 5W total.

For purposes of the other calculations we want to do, lets convert from Power to Energy per Second.

Watts (W) is Energy (J) per unit Time (s)... so 5W average power is 5J delivered in 1 second or 5J/s.

There is 5J delivered in 10K pulses so $5/10,000 = 0.5\text{mJ}$ per pulse (aka 500μJ/pulse).

Oh, but wait, while we now know that there is 500μJ of energy in each pulse, we want to go back to Power and determine the Peak Power, which is the power in each pulse (with assumptions as to pulse shape). To do that



we must have the pulse width. The question in plain language is: "over what time is a single 500μJ pulse delivered?"

In this case, and a common specification of pulse width, we are told the pulses are 10ns wide. This is interesting on several levels but not the least of which might be a consideration of duty cycle which is how much of the time is the laser energy present? Well, 10K pulses per second that are 10ns wide each means $(10 \times 10^3) \times (10 \times 10^{-9})$ yields 100×10^{-6} seconds. The laser is only "on", pulsing energy, for 100μs out of each second, meaning the laser is NOT putting out energy 99.99% of the time!

This "duty cycle" consideration should result in concern as the 5W of total power are delivered over 0.01% of each second. Which should indicate that during that "on time" it seems possible that some very brief but very high powers might be reached. Which is in fact the case, which is why we then ask what the Peak Power is?

So now we know the Average Power but, what might be the Peak Power, or the Power per Pulse?

In this example, which is again, not unusual, we have 500μJ being delivered in 10ns pulses.

Converting back to Power (Watts) its 500×10^{-6} Joules / 10×10^{-9} seconds = 50×10^3 W or 50K Watts.

To be clear here, the Peak Power in each pulse is 50,000 Watts! It just doesn't last long.

Next question? What is the Power Density? We want to know how many Watts per Unit Area.

When considering Power Density you are working with units like "Mega Watts per Centimeter Squared" (MW/cm²) or something similar.

To get to Power Density we need know in what Area are we trying to cram those 50KW of Peak Power? To do that we need the area of the fiber core. A round fiber core has Area = $\pi \cdot r^2$, so, for a 100μm fiber core diameter, aka, 0.01cm (for somewhat arbitrary reasons Pulsed Power Density is typically using area units of cm² whereas CW Power Density will use areas units of mm²), we get:

$$A = 3.14159 \cdot 0.005^2 = 0.0000785\text{cm}^2$$



And so... this example is delivering 50K Watts Peak Power per pulse into an area of 0.0000785cm^2 and dividing Power by Area you get: $50 \times 10^3 \text{ W} / 7.85 \times 10^{-5} \text{ cm}^2 = 6.36 \times 10^8 \text{ W/cm}^2$... said in plain language as "6 point 36 times ten to the eighth watts per square centimeter..."

But is also 636 MW/cm^2 said as "636 Mega Watts per centimeter squared!"

From lowly 5W we end up with a very high-power application with many difficult hurdles, not the least of which is the consideration of the Laser Induced Damage Threshold (LIDT) of the materials we are considering. For the purposes of this memo we will only address the LIDT of a Synthetic Fused Silica fiber itself.

Laser Damage Threshold in Silica:

Where high power laser energy is involved, you must account for the damage threshold of the material the optical fiber is made of, in this case Synthetic Fused Silica. The entire topic of Laser Induced Damage Threshold (LIDT) is extremely hard to pin down. It is not that this topic hasn't been researched at length, but lasers rarely have nicely uniform, homogenous beam profiles. Thus, the total energy across a spot might be well within the theoretical LIDT of the fiber but a spike or "hot spot" might result in localized energy densities far exceeding the allowable LIDT.

As a rule of thumb, the fused silica core of an optical fiber can accept a pulsed laser input (within the wavelength region of 400nm-2000nm) with an energy density of $\sim 1.5 \text{ GW/cm}^2$. If the laser is a CW laser within that same wavelength region, the allowable energy density is perhaps $\sim 1.5 \text{ MW/cm}^2$. This is a 3 orders of magnitude difference. Why? The mechanisms of damage are different.

First, we note again here, as we noted above, that often energy density for CW lasers is arbitrarily, but more typically, given in area units of mm^2 not cm^2 , so, in mm^2 the "allowable" energy density in the fiber, as noted above, would be about 15 KW/mm^2 .

Why the difference in LIDT for CW vs Pulsed Power lasers? For the pulsed laser, the primary damage mechanism will be dielectric breakdown: an electron avalanche is formed due to heating of free electrons by the optical field when the polished fused silica endface is exposed to high peak power densities. For the CW laser, The key factor in whether or not an optic damages when exposed to CW radiation, is how fast it can dissipate the continuously applied heat. In this case unlike pulsed damage, threshold



values depend on average power, thermal diffusivity, thermal conductivity and spot size.

As with all “rules of thumb,” exceptions exist. However, it should be noted that in most cases, the exceptions will result in a lower LIDT – rarely can these guidelines be exceeded. When it seems you may have exceeded these guidelines what you may have done is spread the energy out in time by using a pulse dispersive device like a waveguide taper.

This note on LIDT addresses the bulk glass, it does not address the difficulty of getting such powers into the glass of the fiber itself which is a topic for another memo and which would include a discussion on the control of spot size, NA and considerations of “end capping” to distribute energy over a larger area for input.